# HEAT TREATABLE STEELS AND PRECIPITATION HARDENING STEELS

## Available Product Shapes

Flat Bar

## Product Description

Böhler V330SH – Alloy 4130

## Properties

Cr Mo steel for applications requiring high tensile and toughness values in the heat treated condition. The molybdenum addition prevents the steel from being susceptible to temper brittleness.

| Material designation | |
|---|---|
| 1.7220 | SEL |
| Alloy 4130 | Market grade |

| Standards | |
|---|---|
| 6345<br>6350 | AMS |

## Chemical composition

| C | Si | Mn | Cr | Mo |
|---|---|---|---|---|
| 0.32 | 0.30 | 0.50 | 1.10 | 0.20 |

For more information see www.voestalpine.com/bohler-edelstahl

**voestalpine BÖHLER Edelstahl GmbH & Co KG**
Mariazeller Straße 25
8605 Kapfenberg, AT
T. +43/50304/20-0
E. info@bohler-edelstahl.at
www.voestalpine.com/bohler-edelstahl

voestalpine
ONE STEP AHEAD.