

> Other Oil and Gas + CPI comps.

# TITANIUM AND TITANIUM ALLOYS

### **Available Product Variants**

Plates

## **Product Description**

Bohler L514 is a non-alloyed grade with high corrosion resistance in various environments and excellent ductility with good mechanical properties.

#### **Properties**

- Good strength at high elongation and excellent corrosion resistance in strong oxidizing and mild reducing environments.
- Good weldability and low thermal expansion, biocompatible.

## Applications

- > Medical
- > Medical Instruments & Implants
- > CPI (incl. LNG, Urea) > Comp. for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)

# **Technical data**

Material designation		Standards	
3.7065	SEL	B265	ASTM
R50700	UNS	F67	
Grade 4	Market grade	17850	DIN
		17860	DIN
		ISO 5832-2	EN ISO
		VdTÜV-WB230/1	Others

# Chemical composition (wt. %)

С	Fe	Ν	0	н	Others
max. 0.08	max. 0.40	max. 0.05	max. 0.5	max. 0.015	max. 0.1

Related to ASTM B265

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0 E. info@bohler-edelstahl.at https://www.voestalpine.com/bohler-edelstahl/de/

